



Krytox™ GPL-407

Performance Lubricants

Ultrahigh Temperature Grease

Product Information

Krytox™ GPL-407 grease from Chemours is made using a non-melting thickener, instead of the normal Krytox™ PTFE. This change from PTFE to silica boosts the temperature capability of the grease from approximately 316 °C (600 °F) to an upper limit determined by the evaporation/breakdown temperature of the oil. Krytox™ GPL-407 is made from Krytox™ GPL-107 oil, which, with proper ventilation, can withstand up to 399 °C (750 °F) and higher temperatures for brief periods. With replenishment/re-lubrication, it can last longer. While Krytox™ GPL-407 is not meant to replace the Krytox™ GPL-200 series at temperatures below 288–316 °C (550–600 °F), it does extend the range for using fluorinated greases to beyond the 316 °C (600 °F) limit of PTFE and Teflon™ thickened greases. Krytox™ GPL 407 has higher oil separation than PTFE thickened greases and, therefore, might not last as long under equivalent conditions.

Standard NLGI Grade	#2 Penetration
Base Oil Viscosity, cSt	
20 °C (68 °F)	1600
40 °C (104 °F)	440
100 °C (212 °F)	42
204 °C (400 °F)	6
260 °C (500 °F)	3

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit krytox.com or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2016 The Chemours Company FC, LLC. Krytox™, Teflon™, and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: H-58527-1

C-10680 (2/16)

